

TAYWOOD ENGINEERING LIMITED

Technology Park
Suite 2, 14 Brodie Hall Drive
Bentley Western Australia 6102
PO Box 1021, Bentley Delivery Centre Western Australia 6983
Tel (08) 9470 1511 Fax (08) 9470 1279
Email: telper@taywood.aust.com
A.R.B.N. 009 474 079

May 12, 2001

Coefficient of Friction test was performed in accordance with ASTM standard.

ASTM Test Results:

Coefficient of Friction:

(ASTM D 1894 93) Dry Static 0.91 Dynamic 0.89

(ASTM D 189493) Wet Static 1.29 Dynamic 1.18